



## Liquid Pigments FEPREN L

Liquid Pigments FEPREN L - Typical Qualitative Parameters

	Reds			Black	Browns			Yellow	Orange	Green	Blues	White
	TP100	TP200	TP303	B610	SHD416	SHD430	THD450	Y710	OG980	G820	LB1	TiO <sub>2</sub> -SL
Dry Matter Content [%]	59-61	59-61	59-61	48-52	59-61	59-61	58-61	44-46	47-49	64-66	59-61	64-66
Density [kg/m <sup>3</sup> ]	1850-1950	1850-1950	1850-1950	1600-1700	1800-1950	1800-1900	1740-1860	1450-1550	1550-1650	2000-2100	1900-2000	1930-2010
pH of the Slurry	7.5-9.0	7.5-9.0	7.5-9.0	7.0-10.0	7.5-9.0	7.0-10.0	7.5-9.0	7.0-10.0	7.0-10.0	7.0-9.0	7.0-9.5	8.0-10.0
Viscosity max. [s] Ford Crucible	50	50	50	50	50	50	50	50	50	50	50	75
Residue on Sieve max. [%]	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Colouring Power vs. Standard [%]	±5	±5	±5	±5	±5	±5	±5	±5	±5	±5	±5	±5
Stability min. [months]	6	6	6	6	6	6	6	4	4	6	6	4